Durability of Tropical Woods

By SHOJI AMEMIYA and SHOSHIRO MATSUOKA

Wood Utilization Division, Forestry and Forest Products Research Institute

Since 1964, the Forestry and Forest Products Research Institute has conducted a series of comprehensive studies on the wood properties and processing suitabilities of timbers from Southeast Asia and the Pacific regions.

The authors have taken over a portion of the study on wood properties of the timbers and have evaluated the durability of the timbers.

Woods of about one hundred species from Southeast Asia and the Pacific regions were selected for the test. Most species among them were sampled from markets in Japan, and had been unknown or less-known in Japanese wood industries at the time they were chosen for the tests. Several additional species which had already utilized in Japan were also included to compare the results with those of other species.

The two methods were adopted to evaluate the durability of tropical woods in our test. The one was the sawdust block method in laboratory authorized in Japanese Industrial Standard (JIS), and by this method an average weight loss of each species by fungal attack was measured. The other was the stake test method in field known by research groups of wood preservation, and by the method an average life of each species stake as affected by the damage due to fungal and termite attacks in field was determined.

Samples used for both methods were taken from two positions: one is at 2-3 cm from bark and the other at 60% in relative distance from pith to bark on radial direction of log. The former is called as sapwood, and the latter as heartwood in our test.

Grading of the durability of tropical woods depended upon the durability of heartwood, because the sapwood of most species of them had low durability.

Natural resistance of tropical woods to fungal attack in laboratory

The natural resistance of each species to fungal attack is determined by exposing them in the form of small blocks of $20 \times 20 \times 20$ mm to the action of pure cultures of wood destroying fungi during two months. In this method, the sawdust medium to culture the wood destroying fungi is composed of some beech sawdust, distilled water as twice as the sawdust weight, and 1% glucose and 0.2% peptone to the sawdust in weight. The test fungi were three species, Tyromyces palustris (brown rot), Coriolus versicolor (white rot), and Pyconoporus coccineus (white rot). In every bottle, three blocks are placed on the sawdust medium in which each test fungus is grown, as shown in Plate 1. After the blocks have been introduced, the bottles are closed by means of a screw lid. The bottles are mostly allowed to stand for two months at 26 to 28°C. The blocks in the bottle are attacked by the test fungi during two months. A weight loss of each block was used as a measure of rate of decay.



Plate 1. Sawdust block method

		Common name	Position*	Specific gravity in air dry	T. palustris	C. versicolor	P. coccineus
	1.	Agathis	S	0.41	23.0	2.1	8.1
			н	0.43	2.2	0.7	0
	2.	Alstonia	S	0.44	0.8	12.7	14.6
			Н	0.44	17.8	10.2	15.8
	3.	Apitong	S	0.63	4.1	14.5	14.4
			н	0.69	7.4	8.3	7.6
	4.	Balau	S	0.85	2.8	4.8	2.8
			н	0.99	0	0	1.4
	5.	Bangkirai	S	0.84	1.2	0.7	1.4
			н	0.90	1.0	1.2	1.1
	6.	Borneo oak	S	0.95	0	1.4	3.3
			н	1.01	0	0.7	1.6
	7.	Calophyllum	S	0.69		10.2	8.3
			н	0.64	0	3.2	1.4
	8.	Campnosperma	S	0.58	7.0	14.7	18.0
			H	0.50	15.8	22.6	28.3
	9.	Canarium	S	0.55	17.5	25.7	29.4
			н	0.53	17.7	24.5	22.6
	10.	Celtis	S	0.64	27.6	16.1	31.9
			H	0.63	25.6	19.5	34.6
	11.	Champaka	S	0.47	7.8	9.5	13.8
			н	0.50	0	0.3	0
	12.	Chhoeuteal bangkuoi	S	0.65	2.8	14.9	
	1427227	1/222/02/1/1/1/1/1/1/1/1/1/1/1/1/1/1/1/1	н	0.75	1.4	4.3	0 <u></u>
	13.	Chhoeuteal sar	S	0.60	1.3	17.0	2
	312	T :	H	0.75	3.2	7.4	
	14.	Erima	5 Ц	0.41	1.0	15.6	19.6
	15	Ciam	n c	0.30	4.9	0.0	9.7
	10.	Giam	н	0.98	0.4	0.5	0
	16.	Telutong	S	0,40	3.5	12.6	19.9
	100.00	J	Ĥ	0.41	5.0	18.6	29.5
	17.	Jongkong	S	75-70			27782278 1
1			н	0.52	0	16.2	16.8
54	18.	Kapur	S	ter state of the s			State of the second sec
			н	0.60	0	3.3	7 <u>2000</u>
	19.	Karas	S	0.43	19.4	14.9	31.0
	72527	1228 S. H.	н	0.41	25.0	18.1	38.8
	20.	Kelat	S	0.68	0	8.3	12.4
	01	T-ladama	H C	0.76	0	1.3	2.0
	21.	Keledang	ъ н	0.58	6.5	13.9	20.9
	22	Kerning	S	0.33	0.5	10.2	23.0
75		iteruing	н	0.77	2.0	7.3	
	23.	Koki khsach	S	0.75	0.9	4.8	-
	1.5627677647	- 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 199 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999 - 1999	н	0.85	1.5	1.6	
	24.	Komnhan	S	0.60	3.4	5.0	
			н	0.77	1.6	2.1	
	25.	Labura	S	0.47	14.6	14.5	22.9
			H	0.49	21.9	15.4	13.0
	26.	Light red meranti	S	0.53	4.2	1.4	0
			Н	0.46	0	0.2	0
	27.	Nato	S	0.69	1	10.8	9.6
			H	0.68	0	0.5	1.1

Table 1. Percentage of weight loss caused by decay

	Common name	Position*	Specific gravity in air dry	T. palustris	C. versicolor	P. coccineus
28.	New Guinea basswood	S	0.40	8.1	16.5	18.8
		Н	0.34	11.8	16.5	21.9
29.	Phdiek	S	0.65	8.3	11.7	
		н	0.72	1.6	2.1	
30.	Ramin	S	2000 COD			Contra C
		н	0.66	25.5	19.0	26.8
31.	Red lauan	S	0.62	2.4	10.8	10.9
		H	0.50	2.6	2.2	0
32.	Resak	S	0.64	3.2	0	1.7
		н	0.79	0	0.5	0
33.	Rong leang	S	1.04	2.0	5.0	
	Construction and a company of the	H	1.15	3.4	2.7	
34.	Ro yong	S				
	A 1573	н	0.35	11.5	13.9	
35.	Srol kraham	S	0.43	14.7	7.5	<u></u>
		H	0.49	0.6	7.3	
36.	Taun	S	0.65	6.5	12.2	9.5
		н	0.59	2.3	4.2	2.7
37.	Teraling	S	100	10 <u></u>	6.11.11.4	2 <u>114</u>
		н	0.65	0	4.0	3.8
38.	Terminalia	S		3 		5. 810
		н	0.53	2.9	12.2	14.3
39.	White meranti	S	0.62	5.2	10.6	6.0
		Н	0.60	1.1	2.1	1.2
40.	White siris	S	in the second se	3 113		0
		н	0.43	7.0	15.5	16.8

S: Samples taken from a position of 2-3 cm from bark on radial direction.

H: Samples taken from a position of 60% in relative distance from pith on radial direction.

The average weight losses of main species caused by three fungi in this method are shown in Table 1.

The weight losses in sapwoods of most species among them were higher than those in heartwoods. The weight loss in heartwoods caused by brown rot was approximately similar to that caused by white rot in case of Alstonia, Apitong and Bangkirai, but the former is lower than the latter in Campnosperma Jelutong, Jongkong, Red lauan and White siris, while the former was higher than the latter in Labura.

Average life of tropical wood stakes as affected by fungal and termite attacks in field

The stakes used in this stake test were 3 by 3 by 60 cm in size. Number of stakes for each species was at least ten for sapwood and heart-



Plate 2. Stake test field

wood, respectively. The stakes were set in an upright position with about half of their length in ground. The inspection of all stakes in the field has been carried out once a year. In this inspection, the stakes were individually removed from the test field, inspected and then returned to their original place unless their condition indicated removal. A view of the stake test



Table 2. Service life on the stake test



Plate 3. Appearance of damage

and the condition of damage on a tropical wood stake are shown in Plate 2 and 3, respectively.

Following the inspection by observation, the stakes were graded according to decay and termite attacks, as follows;

Grade Observed condition

- 0 sound
- 1 partial slight damage
- 2 whole slight damage
- 3 condition of 2 with partial severe damage
- 4 whole severe damage
- 5 destroyed

In evaluating a service life prior to 100% removal of stakes, it has been noted that an average life can approximately be estimated by knowing the time when an average grade of the stakes as a group has reached 2.5. The average lives of main species stakes in the field are shown in Table 2.

Sapwood stakes of Sugi and Hinoki in Japanese species have shown an average life of 4.5 and 5.5 years, while their heartwood stakes have shown an average life of 6.0 and 7.0 years. In tropical species, the heartwood stakes of Bankirai, Giam, Koki khsach, Resak and White meranti, etc. showed the longest average life of 8 years or over 8 years, while heartwood stakes of Agathis, Jelutong, Karas and Labura showed the shortest average life of 1 to 2 years. Other species showed an average life of 3 to 7 years.

	Ton a survey servey a survey a survey a survey as	Service life (years)		
	.ommon name	S	н	
1.	Agathis	1.5	1.5	
2.	Alstonia	2.0	2.0	
3.	Apitong	3.5	4.5	
4.	Balau		9.0*	
5.	Bangkirai		9.0*	
6.	Borneo oak	-	9.0*	
7.	Calophyllum		5.0	
8.	Campnosperma		2.0	
9.	Canarium	1000	2.0	
10.	Celtis	2.0	2.0	
11.	Champaka		2.0	
12.	Chhoeuteal bangkuoi	4.0	7.0	
13.	Chhoeuteal sar	2.5	5.0	
14.	Erima	-	3.5	
15.	Giam	-	9.0*	
16.	Jelutong		1.5	
17.	Jongkong	1	4.0	
18.	Kapur	-	7.0	
19.	Karas	s :	1.0	
20.	Kelat		7.5	
21.	Keledang	1	3.0	
22.	Keruing	3.5	5.0	
23.	Koki khsach		11.0*	
24.	Komnhan	5.0	11.0*	
25.	Labura	2000	1.5	
26.	Light red meranti	-	6.0	
27.	Nato		4.0	
28.	New guinea basswood		2.5	
29.	Phdiek		7.0	
30.	Ramin		2.5	
31.	Red lauan		4.0	
32.	Resak		8.0	
33.	Rong leang	8.0	11.0*	
34.	Ro yong		2.0	
35.	Srol kraham		5.5	
36.	Taun		4.0	
37.	Teraling	-	7.0	
38.	Terminalia		3.0	
39.	White meranti	4.0	8.0	
40.	White siris		2.5	

* The species have continued to perform well after service years in the Table.

Relation between the average weight loss by fungal attack in laboratory and the average life in field

In order to know whether is it possible or

not to estimate the average life in the field in a short time from the results obtained in the laboratory, the relation between the average weight loss of small blocks by fungal attacks in the laboratory and the average life of stakes in the field was studied using the results obtained in this work.

It is supposed that the durability of the small blocks and that of the stakes are same with the same species, because they were sampled from the same timber in each species.

The relation between the average weight loss (in percentage) of the small blocks caused by *Coriolus versicolor* and the average life (in years) of stakes is shown in Fig. 1. The relation was recognized at a high level of significance as shown by the following formula:

y=5.72-0.19x r=0.639 s= ± 1.54 where x: weight loss (%),

y: average life (years)

- r: coefficient of correlation
- s: standard deviation

iaia actio	LUI OII	
Class	Designation	
I	very durable	
II	durable	
III	moderately durable	
IV	non-durable	
v	perishable	

This relation shows that an averaged life for all species before any weight loss occurred was about 6 years. However, the actual length of life differed with different species.

Therefore, it is difficult to grade the durability of individual species based on the results in the laboratory test alone. In order to grade the durability, it is unavoidable to depend upon the results of stake tests, service records or references.

Grading the durability of tropical woods

The durability of tropical woods was graded into five classes according to the results of heartwoods obtained by the sawdust block method in the laboratory and the stake test in the field.

The result is shown in Table 3.

Standards used for grading durability into 5 classes are as follows:

Weight loss (%)	Life (year)
0—3	more than 8
0—5	6-7
less than 15	45
more than 15	2 - 3
more than 20	less than 2





The wood species in class I can be used without preserving treatment in field, but the wood species except class I should be used with preserving treatment in field. The wood

species in class IV and V should be used with preliminary preserving treatment in green log and timber, because of their susceptibility to blue stain.

Class V	1.	Agathis (Agathis sp.)	
	16.	Jelutong (Dyera sp.)	
	19.	Karas (Aquilaria malaccensis)	
	25.	Labura (Anthocephalus cadamba)	
Class IV	2.	Alstonia (Alstonia sp.)	
	8.	Campnosperma (Campnosperma brevipetiolata)	
	9.	Canarium (Canarium sp.)	
	10.	Celtis (Celtis sp.)	
	11.	Champaka (Michelia sp.)	
	14.	Erima (Octomeles sumatrana)	
	21.	Keledang (Artocarpus sp.)	
	28.	New Guinea basswood (Endospermum medullosum)	
	30.	Ramin (Gonvstylus bancanus)	
	34.	Ro yong (Parkia streptocarpa)	
	38.	Terminalia (Terminaria sp.)	
	40.	White siris (Ailanthus sp.)	
Class III	3.	Apitong (Dipterocarbus sp.)	-
	7.	Calophyllum (Calophyllum sp.)	
	13.	Chhoeuteal sar (Dipterocarbus alatus)	
	17.	Iongkong (Dactvlocladus stenostachys)	
	22.	Keruing (Dibterocarbus sp.)	
	27.	Nato (Palaruim sp.)	
	31.	Red lauan (Shorea negrosensis)	
	35.	Srol kraham (Dacrydium elatum)	
	36.	Taun (Pometia pinnata)	
Class II	12.	Chhoeuteal bangkuoi (Dipterocarpus insularis)	
	18.	Kapur (Dryobalanobs sp.)	
	20.	Kelat (Eugenia sp.)	
	26.	Light red meranti (Shorea (Rubroshorea) sp.)	
	29.	Phdiek (Anisoptera glabra)	
	37.	Teraling (Tarrietia sp.)	
	39.	White meranti (Shored (Anphoshorea) sp.)	
Class I	4.	Balau (Shorea (Shorea) sp.)	
	5.	Bangkirai (Shorea (Shorea) sp.)	
	6.	Borneo oak (Quercus sp.)	
	15.	Giam (Cotylelobium sp.)	
	23.	Koki khsach (Hopea pierrei)	
	24.	Komnhan (Shorea hypochra)	
	32.	Resak (Vatica sp.)	
	33.	Rong leang (Tristania sp.)	

Table 3. Classification of decay durability

References

- Matsuoka, S. & Shoji, Y.: The properties of tropical woods. VIII. Relative durability of eight species of Cambodian woods, *Bull. Government Forest Exp. Sta.*, 206, 109-113 (1967) [In Japanese with English summary].
- 2) Matsuoka, S.: The properties of tropical woods XIV. Relative durability of Bangkirai, White meranti and thirteen other wood species grown in Kalimantan and Keruing grown in Malaya. Bull. Gov. Forest Exp. Sta., 230, 165-176 (1970) [In Japanese with English summary].
- Matsuoka, S.: Durability and preservation treatment of tropical species, *Mokuzai Kogyo*[•] 32, (11), 51-56 (1977) [In Japanese].
- Wood Technology Division: The properties of tropical woods. X. Studies of the utilization of the Apitong woods grown in the Philippines (1). Bull. Gov. Forest Exp. Sta., 208, 198-206 (1968) [In]apanese with English summary].
- 5) Wood Technology Division and Forest Products Chemistry Division: The properties of tropical woods. XVI. Study on the utilization of the red lauan wood from the Philippines, Bull. Gov. Forest Exp. Sta., 234, 147–152 (1971) [In Japanese

with English summary].

- 6) Wood Technology Division and F. P. Chemistry Division: The properties of tropical woods. XVII. Studies on utilization of seven species from New Guinea and Solomon Islands. Bull. Gov. Forest Exp. Sta., 244, 187-188 (1972) [In Japanese].
- 7) Wood Technology Division and F. P. Chemistry Division: The properties of tropical woods. XVIII. Studies on the utilization of eight species from Sarawak and New Guinea. Bull. Gov. Forest Exp. Sta., 254, 146-147 (1973) [In Japanese].
- 8) Wood Technology Division and F. P. Chemistry Division: The properties of tropical woods. XIX. Studies on the utilization of ten species from Kalimantan and New Guinea, Bull. Gov. Forest Exp. Sta., 262, 142-144 (1974)[In Japanesc].
- 9) Wood Technology Division and F. P. Chemistry Division: Properties of tropical woods. XX. Studies on the utilization of the nine species from New Guinea and other areas. Bull. Gov. Forest Exp. Sta., 269, 73-74 (1974) [In Japanese].
- 10) Working Group on utilization of tropical woods: Properties of some Papua New Guinea woods, relating with manufacturing processes. III. Physical and chemical properties of some East New Britain woods. Bull. Gov. Forest Exp. Sta., 294, 29-37 (1977) [In Japanese with English summary].